

EPOXY 40 ECO

PICKLING PAINTS BY DIPPING FOR ALL LIQUID PAINTS AND POWDER





PACKAGING:

- 20I dark blue PEHD UN approved drums/ Filled at 25 Kg
- 200l dark blue PEHD UN approved barrel / Filled at 240 Kg
- IBC 1,000l Translucent PEHD UN approved containers/ Filled at 1,240 Kg

A REAS OF APPLICATION

EPOXY 40 ECO is an optimised mixture of dichloromethane and oxygenated solvents in an acid medium.

EPOXY 40 ECO is non-flammable.

This product eliminates thin-layer paints such as epoxy polyester, polyester, acrylics, vinyl and all uncured paints on ferrous or aluminium metals.

APPLICATION

1.Concentration: Ready to use **2.Temperature**: 15°C to 25 °C

3.STANDARD SEQUENCE OF USE: application t temperate

4.RINSING: With high pressure washer

METAL TREATMENT AFTER PICKLING: After rinsing the EPOXY 40 ECO pickled pieces, it is necessary:

- to treat them with OXYPASS to avoid any oxidation of the medium;
- or to treat them with HYPRADEX AP607 to eliminate any oxidation traces;
- or to carry out chemical surface conversion (phosphate treatment, chromic or organic passivation) before their repainting.

REGENERATION OF THE BATH:

- Supplement to level with new product.
- Scrubbing of paint flakes using a sieve.
- * Coverage areas are provided for information only and can be used to assess a project. They are in no way contractual; only tests can define the actual amount of product required depending on the surface to be treated

STORAGE:

Minimum storage temperature: + 10 °C
Maximum storage temperature: + 25 °C

Store in tightly closed containers, protected from air and light. If the product is not used within 12 months from the date of manufacture but storage conditions have been met then additional time may be allocated. In this case, contact our sales department.

PHYSICOCHEMICAL PROPERTIES

Clear liquid – Ocher

pH at 10 g/l : 1 +/- 0,4

Density at 20 °C : 1,25 +/- 0,02 g/cm³

Non applicable

Pure pH

A PPLICATION PRECAUTIONS

- Do not allow any contact with skin or mucous membranes.
- Handle by avoiding splashing.
- Consult the safety data sheet available upon request.

Important: The content of this documentation is the result of our product experience. It can not engage our responsibility for its use in each particular case. It is also essential to carry out preliminary tests. Consult the Material Safety Data Sheet (MSDS)



