

SCALPIK L 13 S

CHLORINE LIQUID STRIPPER FOR BATH STRIPPING





PACKAGING:

- Container IBC HDPE 1000I approved UN 1240 Kg
- Blue 200I HDPE plastic drum approved UN 240 kg
- Jerrican plastic HDPE 20l blue approved UN 25 kg

A REAS OF APPLICATION

Liquid stripper for stripping cellulose, acrylic, polyurethane, epoxy paints and varnishes on steel, aluminum, wood, etc.

It works through the penetration of different sofas of paint and peels the canapés of paint from the support.

The product does not saturate. It is enough to recover the waste of paint to find the bottom of the tank and to adjust the level.

APPLICATION

Pay the SCALPIK L 13 S into the pickling tank. Dip the pieces to be stripped with the appropriate equipment. Allow time for stripping paint layers. Remove the bathing pieces and clean them at high pressure. To have a constant level of product in the bath, it will be sufficient to add the new product to adjust the level.

* Coverage areas are provided for information only and can be used to assess a project. They are in no way contractual; only tests can define the actual amount of product required depending on the surface to be treated

STORAGE:

- Minimum storage temperature: none
- Maximum storage temperature: + 40 °C

Store in tightly closed containers, protected from air and light. If the product is not used within 12 months from the date of manufacture but storage conditions have been met then additional time may be allocated. In this case, contact our sales department.

PHYSICOCHEMICAL PROPERTIES

- Colorless liquid
- Density to 20°C: 1.285 +/- 0.05 g/cm³
- Flash point: not flammable
- pH:1

PPLICATION PRECAUTIONS

PROTECTION OF PERSONS: Avoid contact with eyes and skin. In case of contact, wash immediately with water.

Do not breathe vapors. Wear appropriate gloves, eyeglasses and protective clothing and work in a ventilated environment. Handle avoiding projections. For safe use, consult the safety data sheet

Important: The content of this documentation is the result of our product experience. It can not engage our responsibility for its use in each particular case. It is also essential to carry out preliminary tests. Consult the Material Safety Data Sheet (MSDS)





